



Cup 1PE

Datasheet

Property	Units	Standard	Tolerance	200+15	215+15	235+15	260+15	285+15
				Value				
Grammage	g/m ²	ISO 536		215	230	250	275	300
PE reverse	g/m ²	Mill method		15	15	15	15	15
Thickness μ m	Microns	ISO 534		283	308	338	382	422
Moisture (%)	Percent	ISO 287		8.0	8.0	8.5	8.5	9.0
Baseboard:								
Grammage	g/m ²	ISO536	\pm 4%	200	215	235	260	285
Thickness μ m	Microns	ISO 534	\pm 4%	273	298	228	372	412
Stiffness MD Taber 15°	mN.m	ISO 2493	\pm 15%	6.9	9.4	12.1	15.6	20.4
Stiffness CD Taber 15°	mN.m	ISO 2493	\pm 15%	2.8	3.8	4.9	6.3	8.2
Stretch CD %	Percent	ISO 1924-3		5.0				

Voor andere g/m² of tweezijdig PE neem contact op met IPP b.v.

IPP b.v. International Paper & Plastic
 Nijverheidsweg 37, 2102 LK HEEMSTEDÉ
 telefoon +31 (0)23 - 303 57 00
www.ipp.nl