



Cup 2PE

Datasheet

Property	Units	Standard	Tolerance	12+185+15	12+200+15	12+215+15	12+235+15	12+260+15	12+285+15
				Value					
Grammage	g/m ²	ISO 536		212	227	242	262	287	312
PE topside	g/m ²	Mill method		12	12	12	12	12	12
PE reverse	g/m ²	Mill method		15	15	15	15	15	15
Thickness μ m	Microns	ISO 534		270	295	320	350	390	430
Moisture (%)	Percent	ISO 287		8.0	8.0	8.0	8.5	8.5	9.0
Baseboard:									
Grammage	g/m ²	ISO536	\pm 4%	185	200	215	235	260	285
Thickness μ m	Microns	ISO 534	\pm 4%	252	277	302	332	372	412
Stiffness MD Taber 15°	mN.m	ISO 2493	\pm 15%	5.1	5.9	9.4	12.1	15.6	20.4
Stiffness CD Taber 15°	mN.m	ISO 2493	\pm 15%	2.1	2.8	3.8	4.9	6.3	8.2
Stretch CD %	Percent	ISO 1924-3		5.0					

Voor andere g/m² of eenzijdig PE neem contact op met IPP b.v.

IPP b.v. International Paper & Plastic
 Nijverheidsweg 37, 2102 LK HEEMSTEDÉ
 telefoon +31 (0)23 - 303 57 00
www.ipp.nl