



GC1

Datasheet

Property	Tolerance	Value								
G/m ²	+/- 4%	215	230	245	265	290	305	350	400	450
Thickness	+/- 10%	340	370	400	440	490	520	615	725	840
Bulk (cm ³ /g)		1,58	1,61	1,63	1,66	1,69	1,70	1,76	1,81	1,87
Stiffness MD Taber 15	+/- 15%	7.7	9.8	11.9	15.0	19.7	22.7	34.1	50.8	71.8
Stiffness CD Taber 15	+/- 15%	3.6	4.9	6.0	7.7	10.0	11.6	17.6	26.3	37.1
Brightness	+/- 1	90	90	90	90	90	90	90	90	90
Moisture	+/- 1%	7	7,1	7,2	7,5	7,8	7,8	7,9	7,9	7,9

Test Climate 23 C - 50% RH / All figures mentioned may be subject to technical changes

IPP b.v. International Paper & Plastic
Nijverheidsweg 37, 2102 LK Heemstede
telefoon +31 (0)23 - 303 58 00
www.ipp.nl