



Special Black

Datasheet

Property	Tolerance	Value		
G/m ²	+/- 5%	110	240	300
Thickness μ m	Nominal	140	310	375
Bulk (cm ³ /g)		1,27	1,29	1,25
Burst Kpa	Minimum	220	480	600
	Expected	280	540	730
Cobb (1 min) g/m ²	Nominal	25	25	25
Bendtsen Roughness ml/min	Nominal	1400	1400	1400
Relative Humidity %	+/- 10	50	50	50

Property	Tolerance	Value		
G/m ²	Nominal	780	1110	1480
Thickness μ m	+/- 5%	1000	1500	2000
Bulk (cm ³ /g)		1,28	1,35	1,35
Burst Kpa	Minimum			
	Expected			
Cobb (1 min) g/m ²	Nominal	25	25	25
Bendtsen Roughness ml/min	Expected	2000	2000	2000
Relative Humidity %	+/- 15	50	50	50

Test Climate 23 C - 50% RH / All figures mentioned may be subject to technical changes

IPP b.v. International Paper & Plastic
 Nijverheidsweg 37, 2102 LK Heemstede
 telefoon +31 (0)23 - 303 58 00
www.ipp.nl