

ONBOARD

Special White

Datasheet

Property	Tolerance	Value		
G/m ²	+/- 5%	120	270	350
Thickness μ m	Target	140	315	405
Bulk (cm ³ /g)		1,17	1,17	1,16
Burst Kpa	Minimum	180	405	525
	Expected	300	600	700
Cobb (1 min) g/m ²	Target	25	25	25
	Maximum	35	35	35
Bendtsen Roughness ml/min	100	200	200	200
Dennison Wax Pick / Clear	Minimum	10	10	10
	Expected	14	14	14
Moisture (%)	+/- 0,5	6,5	7,5	7,5

Test Climate 23 C - 50% RH / All figures mentioned may be subject to technical changes

IPP b.v. International Paper & Plastic
 Nijverheidsweg 37, 2102 LK Heemstede
 telefoon +31 (0)23 - 303 58 00
www.ipp.nl